


Dropzone Power 18 mm is an flooring system that is intended for heavy weights and rigorous training. It provides comfort and durability for the toughest workouts.



## **Warranty Protection**

25-year comprehensive product coverage. Refer to sample warranty document for complete coverage details.

### **Environmental Facts**

For environmental facts, contact Tarkett Sports Technical Service at 770-712-8540.

### **Maintenance Instructions**

For a complete maintenance guide, contact Tarkett Sports Technical Service at 770-712-8540.

### **Installation Methods**

- Beybond 50 Adhesive: installation using Beybond 50 two-part polyurethane adhesive, which allows moisture tolerance of up to 92% relative humidity per ASTM F2170.
- Dropzone Power can be installed using Tarkett Sports' solvent-free Multi-Poxy adhesive. Multi-Poxy is not only safer for the health of installers, it has a high resistance to moisture (98% RH per ASTM F2170) and superior bond strength.
- If conditions require a moisture barrier, Dropzone Power can be installed with Tarkett Sports' Tarkolay. This system requires no moisture testing.

### **Technical Characteristics**

Property	Standard	Value
Slip Resistance	ASTM D2047	> 0.8
Tensile Strength	ASTM D412	> 265 psi
Abrasion Resistance	ASTM D3389 / EN 649	< 35 g (2,000 cycles)
Density	ASTM D3676	68.3 lbs./cubic foot
Flammability	_	Pass
Tear Resistance	_	Elongation at break 1.52
Surface Texture	_	Slight
VOC Compliance	ASTM D5116	Passed (CA Section 01350)
Total Thickness	_	18 mm (0.709")
Layers	_	Single Layer
Roll Length	_	15'
Roll Width	_	4' (± 0.75")
Weight	_	3.75 lbs./sq. ft.

# **Thickness Options**

Standard thickness is 18 mm (0.709").

888.364.6541 tarkettsportsindoor.com

Compatible substrates include: properly constructed and prepared concrete, wood, asphalt, and cementitious underlayments. Refer to current installation guidelines, ASTM F710, ACI 302.2R, and other industry standard recommendations for more information. Tarkett Sports reserves the right to modify these specifications without affecting their compliance with standards. Some results may vary in relation to certain flexibilities found within specified testing procedures and manufacturing tolerances.



## **Available Colors for Dropzone Power**

## **Group 1**



Black DZ00

## Group 2 - 10% Color



# Group 3 - 20% Color



### **CUSTOM 85% COLOR IS AVAILABLE UPON REQUEST**

The colors presented here are representations only. An actual sample is recommended for exact color evaluation and matching.